




# Basic Quality Statistical Summary Report

**Plant** 1030-Haines City Mine (FDOT Pit #16-024)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 08/16/2022 - 08/23/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	2	100.0	0.00	95-100	95-100
#8 (2.36mm)	2	99.7	0.00	85-100	85-100
#16 (1.18mm)	2	92.8	0.21	65-98	65-100
#30 (0.6mm)	2	60.4	0.07	25-75	>25
#50 (0.3mm)	2	31.8	4.45	5-44	5-45
#100 (0.15mm)	2	7.6	1.34	0-10	0-10
#200 (75µm)	2	0.0	0.07	0-4	0-4
Pan	2	0.0	0.00		
FM	2	2.08	0.057	1.8-2.2\2	
Total Moisture	2	4.1	0.00	0-5	0-6



**Query** Query Selections  
 Date Created 08/23/2022  
 Date Range 08/16/2022 - 08/23/2022  
 Plant Haines City Mine (FDOT Pit #16-024)  
 Sample Type Shipping