




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 09/11/2022 - 09/17/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	8	100.0	0.00	95-100	
#8 (2.36mm)	8	99.9	0.04	85-100	
#16 (1.18mm)	8	94.6	0.58	65-97	
#30 (0.6mm)	8	66.2	2.98	25-75	
#50 (0.3mm)	8	32.4	6.04	5-40	
#100 (0.15mm)	8	2.4	0.35	0-7	
#200 (75µm)	8	0.1	0.10		
Pan	8	0.0	0.00		
FM	8	2.04	0.095	1.82-2.18\2	1.8-2.2



**Query** Query Selections  
 Date Created 09/21/2022  
 Date Range 09/11/2022 - 09/17/2022  
 Plant Green Bay Mine (FDOT Pit #16-608)  
 Sample Type Shipping