




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 09/11/2022 - 09/17/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00		95-100
#8 (2.36mm)	5	98.6	0.29		85-100
#16 (1.18mm)	5	87.4	1.28	67-98	65-99
#30 (0.6mm)	5	58.0	4.40	27-79	25-80
#50 (0.3mm)	5	34.6	3.32	7-38	5-40
#100 (0.15mm)	5	4.0	0.92	0-6	0-7
#200 (75µm)	5	0.0	0.04		0-4
Pan	5	0.0	0.00		
FM	5	2.18	0.088	1.87-2.18\2	1.85-2.2



Query Query Selections
 Date Created 09/21/2022
 Date Range 09/11/2022 - 09/17/2022
 Plant Independent North Mine (FDOT Pit #11-490)
 Sample Type Shipping