




# Basic Quality Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1001-FDOT Concrete Silica Sand Code F01  
**Specification** FLDOT Silica Sand  
**Period** 09/11/2022 - 09/17/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	8	100	0.0	95-100	95-100
#8 (2.36mm)	8	99	0.4	85-100	85-100
#16 (1.18mm)	8	87	1.8	67-96	65-97
#30 (0.6mm)	8	56	3.9	27-68	25-70
#50 (0.3mm)	8	30	2.1	7-33	5-35
#100 (0.15mm)	8	3	0.5	0-7	0-7
#200 (75µm)	8	0	0.4	0-4	0-4
Pan	8	0	0.0		
FM	8	2.24	0.072	2.08-2.4\2.25	2.05-2.45



**Query** Query Selections  
 Date Created 09/21/2022  
 Date Range 09/11/2022 - 09/17/2022  
 Plant Independent North Mine (FDOT Pit #11-490)  
 Sample Type Shipping