



Independent North Mine (FDOT Pit #11-490)
8455 C.R. 474
Clermont, Florida 34714-8339
352-394-7455

09/21/2022

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-490) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

1008-Mason Sand

| Procedure | Sieve/Test | Average | Unit | Mason Sand |
|-------------|---------------|---------|------|------------|
| | #4 (4.75mm) | 100 | % | |
| | #8 (2.36mm) | 100 | % | |
| | #16 (1.18mm) | 100 | % | |
| | #30 (0.6mm) | 99 | % | |
| | #50 (0.3mm) | 90 | % | |
| | #100 (0.15mm) | 16 | % | |
| | #200 (75µm) | 0.1 | % | |
| AASHTO T-27 | FM | 0.96 | | |

Sincerely,

Mario Cardenas
Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 352-394-7455
Cell: 863-528-2335
Fax: 352-394-8730