




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification Mason Sand
Period 09/11/2022 - 09/17/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100	0.0	97-100	
#8 (2.36mm)	4	100	0.0	97-100	
#16 (1.18mm)	4	100	0.0	95-100	
#30 (0.6mm)	4	99	0.0	85-100	
#50 (0.3mm)	4	89	2.2	35-90	
#100 (0.15mm)	4	13	1.3	0-35	
#200 (75µm)	4	0.1	0.10		
Pan	4	0.0	0.00		
FM	4	1.00	0.033	1.05-1.45	1.2



Query Query Selections
 Date Created 09/21/2022
 Date Range 09/11/2022 - 09/17/2022
 Plant Independent North Mine (FDOT Pit #11-490)
 Sample Type Shipping