




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 09/11/2022 - 09/17/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	9	100.0	0.00		95-100
#8 (2.36mm)	9	99.7	0.11		85-100
#16 (1.18mm)	9	95.2	0.84	67-98	65-99
#30 (0.6mm)	9	71.0	3.73	27-79	25-80
#50 (0.3mm)	9	27.5	4.25	7-38	5-40
#100 (0.15mm)	9	4.0	0.99	0-6	0-7
#200 (75µm)	9	0.2	0.10		0-4
Pan	9	0.0	0.00		
FM	9	2.027	0.0886	1.87-2.18\2	1.85-2.2



**Query** Query Selections  
 Date Created 09/21/2022  
 Date Range 09/11/2022 - 09/17/2022  
 Plant Independent South Mine (FDOT Pit#11-298)  
 Sample Type Shipping