




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 10/18/2022 - 10/25/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100.0	0.00	95-100	
#8 (2.36mm)	6	99.9	0.05	85-100	
#16 (1.18mm)	6	95.1	0.46	65-97	
#30 (.6mm)	6	67.4	3.41	25-75	
#50 (.3mm)	6	39.6	4.06	5-40	
#100 (.15mm)	6	2.6	0.53	0-7	
#200 (75µm)	6	0.1	0.12		
Pan	6	0.0	0.00		
FM	6	1.96	0.078	1.82-2.18\2	1.8-2.2
Total Moisture	6	2.9	0.88	1-5	1-5



Query

Query Selections

Date Created 10/25/2022

Date Range 10/18/2022 - 10/25/2022

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping