




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1001-FDOT Concrete Silica Sand Code F01  
**Specification** FLDOT Silica Sand  
**Period** 10/18/2022 - 10/25/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	10	100	0.0	95-100	95-100
#8 (2.36mm)	10	100	0.0	85-100	85-100
#16 (1.18mm)	10	93	0.9	67-96	65-97
#30 (.6mm)	10	59	3.1	27-68	25-70
#50 (.3mm)	10	21	3.7	7-33	5-35
#100 (.15mm)	10	1	0.4	0-6	0-7
#200 (75µm)	10	0	0.0	0-4	0-4
Pan	10	0	0.0		
FM	10	2.26	0.071	2.3	2.1-2.5
Total Moisture	10	3.0	0.35		



**Query**

Query Selections

Date Created 10/25/2022

Date Range 10/18/2022 - 10/25/2022

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping

Agency Florida DOT MAC