



Green Bay Mine (FDOT Pit #16-608)
4949 Sand Mine Road
Davenport, Florida 33897
863-424-0730

10/01/2022

To Whom it may concern,

This material is currently produced at our "Green Bay" facility (FDOT mine #16-608) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#30 (0.6mm)	96	%	
	#50 (0.3mm)	83	%	
	#100 (0.15mm)	7	%	
	#200 (75µm)	0.1	%	

Sincerely,

Mario Cardenas
Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 352-394-7455
Cell: 863-557-0342
Fax: 352-394-8730



10/01/2022

Green Bay Mine (FDOT Pit #16-608)
4949 Sand Mine Road
Davenport, Florida 33897
863-424-0730