




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1008-Mason Sand  
**Specification** Mason Sand  
**Period** 10/18/2022 - 10/25/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	1	100		97-100	
#8 (2.36mm)	1	100		97-100	
#16 (1.18mm)	1	100		95-100	
#30 (.6mm)	1	97		85-100	
#50 (.3mm)	1	73		35-90	
#100 (.15mm)	1	3		3-35	
#200 (75µm)	1	0.1			
Pan	1	0.0			
FM	1	1.26		0.9-1.4\1.2	
Total Moisture	1	2.7		0-5.5	0-6



**Query**

Query Selections

Date Created 10/25/2022

Date Range 10/18/2022 - 10/25/2022

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping