




Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 10/18/2022 - 10/25/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	2	100.0	0.00	95-100	95-100
#8 (2.36mm)	2	99.8	0.14	85-100	85-100
#16 (1.18mm)	2	95.8	1.20	65-98	65-100
#30 (.6mm)	2	72.8	5.09	25-75	≥25
#50 (.3mm)	2	44.1	4.10	5-44	5-45
#100 (.15mm)	2	9.2	0.85	0-10	0-10
#200 (75µm)	2	0.1	0.00	0-4	0-4
Pan	2	0.0	0.00		
FM	2	1.78	0.113	1.8-2.2\2	
Total Moisture	2	3.9	0.00	0-5	0-6



Query

Query Selections

Date Created 10/25/2022

Date Range 10/18/2022 - 10/25/2022

Plant Haines City Mine (FDOT Pit #16-024)

Sample Type Shipping