




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FLDOT Silica Sand
Period 10/18/2022 - 10/25/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	8	100	0.0	95-100	95-100
#8 (2.36mm)	8	98	0.5	85-100	85-100
#16 (1.18mm)	8	86	2.1	67-96	65-97
#30 (.6mm)	8	54	5.6	27-68	25-70
#50 (.3mm)	8	28	3.0	7-33	5-35
#100 (.15mm)	8	3	0.5	0-7	0-7
#200 (75µm)	8	0	0.0	0-4	0-4
Pan	8	0	0.0		
FM	8	2.30	0.099	2.08-2.4\2.25	2.05-2.45



Query

Query Selections
Date Created 10/25/2022
Date Range 10/18/2022 - 10/25/2022
Plant Independent North Mine (FDOT Pit #11-490)
Sample Type Shipping