




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification
Period 10/18/2022 - 10/25/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	3	0	0.0		
#8 (2.36mm)	3	0	0.0		
#16 (1.18mm)	3	0	0.0		
#30 (.6mm)	3	1	0.6		
#50 (.3mm)	3	9	1.7		
#100 (.15mm)	3	83	6.7		
#200 (75µm)	3	99.7	0.35		
Pan	3	100.0	0.00		
FM	3	0.93	0.076		
Total Moisture	3	7.3	3.28		



Query

Query Selections

Date Created 10/25/2022

Date Range 10/18/2022 - 10/25/2022

Plant Independent North Mine (FDOT Pit #11-490)-1050

Sample Type Shipping