




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 10/18/2022 - 10/25/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	8	100.0	0.00		95-100
#8 (2.36mm)	8	99.6	0.12		85-100
#16 (1.18mm)	8	94.2	1.19	67-98	65-99
#30 (.6mm)	8	65.9	6.38	27-79	25-80
#50 (.3mm)	8	25.4	5.81	7-38	5-40
#100 (.15mm)	8	3.5	1.74	0-6	0-7
#200 (75µm)	8	0.2	0.13		0-4
Pan	8	0.0	0.00		
FM	8	2.114	0.1402	1.87-2.18\2	1.85-2.2



Query

Query Selections
Date Created 10/25/2022
Date Range 10/18/2022 - 10/25/2022
Plant Independent South Mine (FDOT Pit#11-298)
Sample Type Shipping