




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1008-Mason Sand
Specification Mason Sand
Period 10/18/2022 - 10/25/2022

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	7	100	0.0	97-100	
#8 (2.36mm)	7	100	0.0	97-100	
#16 (1.18mm)	7	100	0.4	95-100	
#30 (.6mm)	7	99	1.8	85-100	
#50 (.3mm)	7	82	7.7	35-90	
#100 (.15mm)	7	15	6.6	0-35	
#200 (75µm)	7	0.5	0.12		
Pan	7	0.0	0.00		
FM	7	1.053	0.1385	1.05-1.45	1.2



Query

Query Selections
Date Created 10/25/2022
Date Range 10/18/2022 - 10/25/2022
Plant Independent South Mine (FDOT Pit#11-298)
Sample Type Shipping