



12/20/2022

To Whom it may concern,

This material is currently produced at Liberty Sand Mine. This material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	99	%	
	#16 (1.18mm)	98	%	
	#30 (.6mm)	93	%	
	#50 (.3mm)	69	%	
	#100 (.15mm)	23	%	
	#200 (75µm)	0.3	%	
ASTM C-136	FM	1.18		

Sincerely,

Mario Cardenas  
Quality Control Manager  
E.R. Jahna Ind, Inc.  
Office: 863-424-0730  
Cell: 863-557-0342  
Fax: 352-394-8730

**Name/Title** Mario Cardenas / Quality Control Manager