




Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 12/27/2022 - 01/03/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100.0	0.00	95-100	95-100
#8 (2.36mm)	4	99.8	0.00	85-100	85-100
#16 (1.18mm)	4	95.6	0.69	65-98	65-100
#30 (.6mm)	4	71.0	1.22	25-75	≥25
#50 (.3mm)	4	44.2	2.20	5-44	5-45
#100 (.15mm)	4	9.4	1.60	0-10	0-10
#200 (75µm)	4	0.1	0.00	0-4	0-4
Pan	4	0.0	0.00		
FM	4	1.80	0.032	1.8-2.2\2	
Total Moisture	4	4.5	0.94	0-5	0-6



Query

Query Selections

Date Created 01/03/2023

Date Range 12/27/2022 - 01/03/2023

Plant Haines City Mine (FDOT Pit #16-024)

Sample Type Shipping