




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification
Period 12/27/2022 - 01/03/2023

| Sieve/Test | Tests | Average | St Dev | Target | Specification |
|----------------|-------|---------|--------|--------|---------------|
| #4 (4.75mm) | 3 | 0 | 0.0 | | |
| #8 (2.36mm) | 3 | 0 | 0.0 | | |
| #16 (1.18mm) | 3 | 1 | 0.6 | | |
| #30 (.6mm) | 3 | 5 | 4.4 | | |
| #50 (.3mm) | 3 | 21 | 11.9 | | |
| #100 (.15mm) | 3 | 90 | 0.6 | | |
| #200 (75µm) | 3 | 99.9 | 0.06 | | |
| Pan | 3 | 100.0 | 0.00 | | |
| FM | 3 | 1.16 | 0.174 | | |
| Total Moisture | 3 | 5.3 | 0.79 | | |



Query

Query Selections

Date Created 01/03/2023

Date Range 12/27/2022 - 01/03/2023

Plant Independent North Mine (FDOT Pit #11-490)-1050

Sample Type Shipping