




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1001-FDOT Concrete Silica Sand Code F01  
**Specification** FLDOT Silica Sand  
**Period** 12/27/2022 - 01/03/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100	0.0	95-100	95-100
#8 (2.36mm)	4	99	0.5	85-100	85-100
#16 (1.18mm)	4	93	0.5	67-96	65-97
#30 (.6mm)	4	58	1.3	27-68	25-70
#50 (.3mm)	4	13	1.7	7-33	5-35
#100 (.15mm)	4	1	0.5	0-7	0-7
#200 (75µm)	4	0	0.0	0-4	0-4
Pan	4	0	0.0		
FM	4	2.362	0.0354	2.08-2.4\2.25	2.05-2.45



**Query**

Query Selections  
Date Created 01/03/2023  
Date Range 12/27/2022 - 01/03/2023  
Plant Independent South Mine (FDOT Pit#11-298)  
Sample Type Shipping