




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1008-Mason Sand
Specification Mason Sand
Period 12/27/2022 - 01/03/2023

| Sieve/Test | Tests | Average | St Dev | Target | Specification |
|--------------|-------|---------|--------|---------------|---------------|
| #4 (4.75mm) | 2 | 100 | 0.0 | 97-100 | |
| #8 (2.36mm) | 2 | 100 | 0.0 | 97-100 | |
| #16 (1.18mm) | 2 | 100 | 0.7 | 95-100 | |
| #30 (.6mm) | 2 | 96 | 2.1 | 85-100 | |
| #50 (.3mm) | 2 | 86 | 3.5 | 35-90 | |
| #100 (.15mm) | 2 | 24 | 1.4 | 0-35 | |
| #200 (75µm) | 2 | 0.6 | 0.14 | | |
| Pan | 2 | 0.0 | 0.00 | | |
| FM | 2 | 0.934 | 0.0742 | 1.05-1.45\1.2 | |



Query

Query Selections
Date Created 01/04/2023
Date Range 12/27/2022 - 01/03/2023
Plant Independent South Mine (FDOT Pit#11-298)
Sample Type Shipping