




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 12/27/2022 - 01/03/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00	95-100	
#8 (2.36mm)	5	99.9	0.05	85-100	
#16 (1.18mm)	5	96.6	0.76	65-99	
#30 (.6mm)	5	65.3	3.16	25-70	
#50 (.3mm)	5	30.3	3.93	5-35	
#100 (.15mm)	5	2.1	0.98	0-7	
#200 (75µm)	5	0.0	0.05		
Pan	5	0.0	0.00		
FM	5	2.06	0.046		
Total Moisture	4	3.7	0.08		



Query

Query Selections
Date Created 01/03/2023
Date Range 12/27/2022 - 01/03/2023
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping