



Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 02/15/2023 - 02/22/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	11	100.0	0.00	95-100	
#8 (2.36mm)	11	99.9	0.05	85-100	
#16 (1.18mm)	11	95.3	0.56	65-97	
#30 (.6mm)	11	64.9	1.00	25-75	
#50 (.3mm)	11	31.2	3.38	5-40	
#100 (.15mm)	11	2.4	0.45	0-7	
#200 (75µm)	11	0.1	0.05		
Pan	11	0.0	0.00		
FM	11	2.06	0.034	1.82-2.18\2	1.8-2.2
Grad Loss	11	0.012	0.0170		
Total Moisture	10	3.8	0.55	1-5	1-5

Query

Query Selections

Date Created 02/22/2023

Date Range 02/15/2023 - 02/22/2023

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping