



Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FLDOT Silica Sand
Period 02/15/2023 - 02/22/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	13	100	0.0	95-100	95-100
#8 (2.36mm)	13	100	0.0	85-100	85-100
#16 (1.18mm)	13	94	1.0	67-96	65-97
#30 (.6mm)	13	59	2.9	27-68	25-70
#50 (.3mm)	13	23	2.8	7-33	5-35
#100 (.15mm)	13	1	0.8	0-6	0-7
#200 (75µm)	13	0	0.0	0-4	0-4
Pan	13	0	0.0		
FM	13	2.23	0.042	2.3	2.1-2.5
Grad Loss	13	0.017	0.0315		
Total Moisture	13	3.1	0.76		

Query

Query Selections

Date Created 02/22/2023

Date Range 02/15/2023 - 02/22/2023

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping