



Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1008-Mason Sand
Specification Mason Sand
Period 02/15/2023 - 02/22/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100	0.0	97-100	
#8 (2.36mm)	5	100	0.0	97-100	
#16 (1.18mm)	5	100	0.5	95-100	
#30 (.6mm)	5	95	4.1	85-100	
#50 (.3mm)	5	82	8.7	35-90	
#100 (.15mm)	5	10	3.5	3-35	
#200 (75µm)	5	0.1	0.00		
Pan	5	0.0	0.00		
FM	5	1.13	0.164	0.9-1.4\1.2	
Grad Loss	5	0.020	0.0186		
Total Moisture	4	6.0	2.24	0-5.5	0-6

Query

Query Selections

Date Created 02/22/2023

Date Range 02/15/2023 - 02/22/2023

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping