



Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 02/15/2023 - 02/22/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00	95-100	95-100
#8 (2.36mm)	5	99.9	0.04	85-100	85-100
#16 (1.18mm)	5	95.5	1.31	65-98	65-100
#30 (.6mm)	5	71.0	5.97	25-75	≥25
#50 (.3mm)	5	39.1	4.58	5-44	5-45
#100 (.15mm)	5	6.9	3.02	0-10	0-10
#200 (75µm)	5	0.1	0.08	0-4	0-4
Pan	5	0.0	0.00		
FM	5	1.88	0.034	1.8-2.2\2	
Total Moisture	5	3.9	1.23	0-5	0-6

Query

Query Selections

Date Created 02/22/2023

Date Range 02/15/2023 - 02/22/2023

Plant Haines City Mine (FDOT Pit #16-024)

Sample Type Shipping