



Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification Mason Sand
Period 02/15/2023 - 02/22/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	2	100	0.0	97-100	
#8 (2.36mm)	2	100	0.0	97-100	
#16 (1.18mm)	2	100	0.0	95-100	
#30 (.6mm)	2	100	0.7	85-100	
#50 (.3mm)	2	86	5.7	35-90	
#100 (.15mm)	2	9	2.8	0-35	
#200 (75µm)	2	0.1	0.00		
Pan	2	0.0	0.00		
FM	2	1.05	0.085	1.05-1.45\1.2	
Total Moisture	2	4.5	0.85	0-5	0-6

Query

Query Selections
Date Created 02/22/2023
Date Range 02/15/2023 - 02/22/2023
Plant Independent North Mine (FDOT Pit #11-490)
Sample Type Shipping