



Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 02/15/2023 - 02/22/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00		95-100
#8 (2.36mm)	5	99.6	0.17		85-100
#16 (1.18mm)	5	92.4	1.57	67-98	65-99
#30 (.6mm)	5	69.7	4.18	27-79	25-80
#50 (.3mm)	5	35.1	3.98	7-38	5-40
#100 (.15mm)	5	3.5	0.69	0-6	0-7
#200 (75µm)	5	0.0	0.04		0-4
Pan	5	0.0	0.00		
FM	5	2.00	0.097	1.87-2.18\2	1.85-2.2
Total Moisture	5	4.2	0.49		

Query

Query Selections
Date Created 02/22/2023
Date Range 02/15/2023 - 02/22/2023
Plant Independent North Mine (FDOT Pit #11-490)
Sample Type Shipping