




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1008-Mason Sand
Specification Mason Sand
Period 02/06/2023 - 02/13/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	3	100	0.0	97-100	
#8 (2.36mm)	3	100	0.0	97-100	
#16 (1.18mm)	3	97	1.0	95-100	
#30 (.6mm)	3	89	2.1	85-100	
#50 (.3mm)	3	77	2.1	35-90	
#100 (.15mm)	3	20	2.1	0-35	
#200 (75µm)	3	0.4	0.06		
Pan	3	0.0	0.00		
FM	3	1.168	0.0600	1.05-1.45\1.2	
Total Moisture	3	7.037	0.9524	0-5	0-6



Query

Query Selections
Date Created 02/13/2023
Date Range 02/06/2023 - 02/13/2023
Plant Independent South Mine (FDOT Pit#11-298)
Sample Type Shipping