



Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 02/15/2023 - 02/22/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100.0	0.00		95-100
#8 (2.36mm)	6	99.6	0.14		85-100
#16 (1.18mm)	6	94.2	0.86	67-98	65-99
#30 (.6mm)	6	68.2	2.45	27-79	25-80
#50 (.3mm)	6	30.0	3.82	7-38	5-40
#100 (.15mm)	6	7.0	1.65	0-6	0-7
#200 (75µm)	6	0.2	0.04		0-4
Pan	6	0.0	0.00		
FM	6	2.010	0.0781	1.87-2.18\2	1.85-2.2
Total Moisture	6	7.057	1.8405		

Query

Query Selections
Date Created 02/22/2023
Date Range 02/15/2023 - 02/22/2023
Plant Independent South Mine (FDOT Pit#11-298)
Sample Type Shipping