



Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 02/15/2023 - 02/22/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100.0	0.00	95-100	
#8 (2.36mm)	4	99.9	0.05	85-100	
#16 (1.18mm)	4	97.1	0.81	65-99	
#30 (.6mm)	4	57.6	5.25	25-70	
#50 (.3mm)	4	23.6	11.24	5-35	
#100 (.15mm)	4	2.0	1.17	0-7	
#200 (75µm)	4	0.0	0.06		
Pan	4	0.0	0.00		
FM	4	2.20	0.176		
Total Moisture	4	3.5	0.62		

Query

Query Selections
Date Created 02/22/2023
Date Range 02/15/2023 - 02/22/2023
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping