



02/01/2023 – 02/28/2023

To Whom it may concern,

This material is currently produced at our "Green Bay" facility (FDOT mine #16-608) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#30 (.6mm)	96	%	
	#50 (.3mm)	82	%	
	#100 (.15mm)	10	%	
	#200 (75µm)	0.1	%	
AASHTO T-27	FM	1.13		
	Grad Loss	0.019	%	
AASHTO T-255	Total Moisture	5.1	%	0.0-6.0

Sincerely,

Mario Cardenas Quality  
Control Manager E.R.  
Jahna Ind, Inc.  
Office: 352-394-7455  
Cell: 863-557-0342  
03/06/2023

Fax: 352-394-8730

**Name/Title**

David Clements / Mine manager