



02/01/2023 – 02/28/2023

To Whom it may concern,

This material is currently produced at our "Haines City" facility (FDOT mine #16-024) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Concrete Sand" product number (1009) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1009-Concrete Sand

Procedure	Sieve/Test	Average	Unit	Concrete Sand
	#4 (4.75mm)	100.0	%	95-100
	#8 (2.36mm)	99.8	%	85-100
	#16 (1.18mm)	95.7	%	65-100
	#30 (.6mm)	71.9	%	≥25
	#50 (.3mm)	40.5	%	5-45
	#100 (.15mm)	7.4%	0-10 % 0-4	
	#200 (75µm)	0.1		
ASTM C-136	FM	1.85		
ASTM C 128	Absorption (Fine)	0.1		
ASTM C-566	Total Moisture	3.7	%	0.0-6.0
ASTM C-128	SPGR Fine (Dry, Gsb)	2.638		
ASTM C-128	SPGR Fine (SSD)	2.641		
ASTM C-128	SPGR Fine (Apparent, Gsa)	2.647		

Sincerely,

Mario Cardenas  
Quality Control Manager  
E.R. Jahna Ind, Inc.  
Office: 352-394-7455  
Cell: 863-557-0342  
Fax: 352-394-8730

Name/Title

David Clements / Mine  
manager