



03/06/2023

1004-Well Point Sand

Procedure	Sieve/Test	Average	Unit	Well Point
	#4 (4.75mm)	100.0	%	95-100
	#8 (2.36mm)	98.6	%	85-100
	#16 (1.18mm)	82.6	%	64-97
	#30 (.6mm)	47.8	%	19-70
	#50 (.3mm)	22.2	%	3-35
	#100 (.15mm)	3.1	%	0-7
	#200 (75µm)	0.08	%	
AASHTO T-27	FM	2.46		2.60-2.90
AASHTO T-255	Total Moisture	3.7	%	

Name/Title

David Clements / Mine manager