



02/01/2023 – 02/28/2023

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-298) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	97	%	
	#30 (.6mm)	90	%	
	#50 (.3mm)	78	%	
	#100 (.15mm)	20	%	
	#200 (75µm)	0.4	%	
ASTM C-136	FM	1.143		
ASTM C-566	Total Moisture	6.788	%	0.000-6.000

Sincerely,

Mario Cardenas Quality
Control Manager E.R.
Jahna Ind, Inc.
Office: 863-424-0730 ext.515
Cell: 863-557-0342

Name/Title

David Clements / Mine manager