



02/07/2023

1004-Well Point Sand

Procedure	Sieve/Test	Average	Unit	Well Point Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	93	%	
	#30 (.6mm)	38	%	
	#50 (.3mm)	7	%	
	#100 (.15mm)	0	%	
	#200 (75µm)	0.0	%	
ASTM C-136	FM	2.61		

Name/Title

David Clements / Mine manager