




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 05/01/2023 - 05/10/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	11	100.0	0.00	95-100	
#8 (2.36mm)	11	99.9	0.05	85-100	
#16 (1.18mm)	11	96.5	0.94	65-97	
#30 (.6mm)	11	76.0	4.07	25-75	
#50 (.3mm)	11	38.6	5.42	5-40	
#100 (.15mm)	11	3.2	0.64	0-7	
#200 (75µm)	11	0.1	0.07		
Pan	11	0.0	0.00		
FM	11	1.86	0.097	1.82-2.18\2	1.8-2.2



**Query**

Query Selections

Date Created 05/10/2023

Date Range 05/01/2023 - 05/10/2023

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping