



05/22/2023

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-490) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Concrete Sand" product number (1009) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1009-Concrete Sand

Procedure	Sieve/Test	Average	Unit	Concrete Sand
	#4 (4.75mm)	100.0	%	95-100
	#8 (2.36mm)	99.7	%	85-100
	#16 (1.18mm)	94.8	%	65-99
	#30 (.6mm)	73.2	%	25-80
	#50 (.3mm)	30.4	%	5-40
	#100 (.15mm)	2.4	%	0-7
	#200 (75µm)	0.1	%	0-4
AASHTO T-27	FM	2.00		1.85-2.20
AASHTO T-255	Total Moisture	7.1	%	
	D10 (ES)	0.1818	mm	
	D50	0.41	mm	
	D60	0.49	mm	
	Cc	0.99		
	Cu	2.68		

Sincerely,

Mario Cardenas  
Quality Control Manager  
E.R. Jahna Ind, Inc.  
Office: 352-394-7455  
Cell: 863-528-2335  
Fax: 352-394-8730



05/22/2023

**Name/Title**

David Clements / Mine manager