



05/22/2023

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-490) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#30 (.6mm)	98	%	
	#50 (.3mm)	76	%	
	#100 (.15mm)	11	%	
	#200 (75µm)	0.1	%	
AASHTO T-27	FM	1.15		
AASHTO T-255	Total Moisture	4.0	%	0.0-6.0
	D10 (ES)	0.1369	mm	
	D50	0.23	mm	
	D60	0.26	mm	
	Cc	0.98		
	Cu	1.86		

Sincerely,

Mario Cardenas
Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 352-394-7455
Cell: 863-528-2335
Fax: 352-394-8730

Name/Title

David Clements / Mine manager



05/22/2023