




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 05/01/2023 - 05/10/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	3	100.0	0.00		95-100
#8 (2.36mm)	3	99.7	0.21		85-100
#16 (1.18mm)	3	96.1	1.17	67-98	65-99
#30 (.6mm)	3	68.2	2.50	27-79	25-80
#50 (.3mm)	3	35.6	1.56	7-38	5-40
#100 (.15mm)	3	3.6	1.68	0-6	0-7
#200 (75µm)	3	0.1	0.00		0-4
Pan	3	0.0	0.00		
FM	3	1.969	0.0565	1.87-2.18\2	1.85-2.2



**Query**

Query Selections  
Date Created 05/10/2023  
Date Range 05/01/2023 - 05/10/2023  
Plant Independent South Mine (FDOT Pit#11-298)  
Sample Type Shipping