



05/22/2023

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-298) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#30 (.6mm)	98	%	
	#50 (.3mm)	75	%	
	#100 (.15mm)	26	%	
	#200 (75µm)	8.8	%	
ASTM C-136	FM	1.000		
ASTM C-566	Total Moisture	4.530	%	0.000-6.000
	D10 (ES)	0.16	mm	
	D50	0.21	mm	
	D60	0.24	mm	
	Cc	0.76		
	Cu	1.74		

Sincerely,

Mario Cardenas
Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 863-424-0730 ext.515
Cell: 863-557-0342



05/22/2023

Name/Title

David Clements / Mine manager