



05/22/2023

To Whom it may concern,

This material is currently produced at our "Ortona" facility (FDOT mine #05-045) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Concrete Sand" product number (1009) is a washed and graded product. Each load is accompanied by an individual ticket.

1009-Concrete Sand

Procedure	Sieve/Test	Average	Unit	Concrete Sand
	#4 (4.75mm)	100.0	%	
	#8 (2.36mm)	99.9	%	
	#16 (1.18mm)	96.7	%	
	#30 (.6mm)	62.0	%	
	#50 (.3mm)	30.4	%	
	#100 (.15mm)	4.5	%	
	#200 (75µm)	0.0	%	
ASTM C-136	FM	2.07		
	Grad Loss	0.000	%	
ASTM C-566	Total Moisture	3.8	%	
	D10 (ES)	0.18	mm	
	D50	0.45	mm	
	D60	0.58	mm	
	D15/D85	0.22		
	Cc	0.87		
	Cu	3.30		

Sincerely,

Mario Cardenas

Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 352-394-7455
Cell: 863-528-2335
Fax: 352-394-8730



05/22/2023

Name/Title

David Clements / Mine manager