



05/22/2023

To Whom it may concern,

This material is currently produced at our "Ortona" facility (FDOT mine #05-045) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	99	%	
	#30 (.6mm)	85	%	
	#50 (.3mm)	51	%	
	#100 (.15mm)	5	%	
	#200 (75µm)	0.1	%	
ASTM C-136	FM	1.60		
	Grad Loss	0.000	%	
ASTM C-566	Total Moisture	3.7	%	0.0-6.0
	D10 (ES)	0.16	mm	
	D50	0.30	mm	
	D60	0.36	mm	
	D15/D85	0.29		
	Cu	2.20		

Sincerely,

*Mario Cardenas*

Quality Control Manager  
E.R. Jahna Ind, Inc.  
Office: 352-394-7455



05/22/2023

Cell: 863-528-2335  
Fax: 352-394-8730

<b>Name/Title</b>	David Clements / Mine manager
-------------------	-------------------------------