



08/03/2023

To Whom it may concern,

This material is currently produced at our "Ortona" facility (FDOT mine #05-045) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Concrete Sand" product number (1009) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1009-Concrete Sand

Procedure	Sieve/Test	Average	Unit	Concrete Sand
	#4 (4.75mm)	100.0	%	
	#8 (2.36mm)	99.9	%	
	#16 (1.18mm)	97.1	%	
	#30 (.6mm)	63.9	%	
	#50 (.3mm)	21.9	%	
	#100 (.15mm)	1.8	%	
	#200 (75µm)	0.0	%	
ASTM C-136	FM	2.15		
ASTM C-566	Total Moisture	3.2	%	

Sincerely,

*Mario Cardenas*

Quality Control Manager  
E.R. Jahna Ind, Inc.  
Office: 352-394-7455  
Cell: 863-528-2335  
Fax: 352-394-8730

**Name/Title**

David Clements / Mine manager