



08/03/2023

To Whom it may concern,

This material is currently produced at our "Ortona" facility (FDOT mine #05-045) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1008-Mason Sand

| Procedure  | Sieve/Test     | Average | Unit | Mason Sand |
|------------|----------------|---------|------|------------|
|            | #4 (4.75mm)    | 100     | %    |            |
|            | #8 (2.36mm)    | 100     | %    |            |
|            | #16 (1.18mm)   | 97      | %    |            |
|            | #30 (.6mm)     | 71      | %    |            |
|            | #50 (.3mm)     | 41      | %    |            |
|            | #100 (.15mm)   | 4       | %    |            |
|            | #200 (75µm)    | 0.1     | %    |            |
| ASTM C-136 | FM             | 1.87    |      |            |
|            | Grad Loss      | 0.000   | %    |            |
| ASTM C-566 | Total Moisture | 3.8     | %    | 0.0-6.0    |

Sincerely,

*Mario Cardenas*

Quality Control Manager  
E.R. Jahna Ind, Inc.  
Office: 352-394-7455  
Cell: 863-528-2335  
Fax: 352-394-8730

Name/Title

David Clements / Mine manager