



08/09/2023

To Whom it may concern,

This material is currently produced at Liberty Sand Mine. This material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	98	%	
	#30 (.6mm)	93	%	
	#50 (.3mm)	79	%	
	#100 (.15mm)	19	%	
	#200 (75µm)	0.4	%	
ASTM C-136	FM	1.12		

Sincerely,

Mario Cardenas
Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 863-424-0730
Cell: 863-557-0342
Fax: 352-394-8730

Name/Title

David Clements / Mine manager