




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 12/22/2023 - 12/29/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00	95-100	
#8 (2.36mm)	5	99.9	0.08	85-100	
#16 (1.18mm)	5	94.6	0.73	65-97	
#30 (.6mm)	5	69.0	2.71	25-75	
#50 (.3mm)	5	36.6	5.98	5-40	
#100 (.15mm)	5	2.3	0.71	0-7	
#200 (75µm)	5	0.0	0.05		
Pan	5	0.0	0.00		
FM	5	1.98	0.082	1.82-2.18\2	1.8-2.2
Total Moisture	5	4.1	1.44	1-5	1-5



Tests: 1 D10(ES): 0.175 D15: 0.194 D30: 0.263 D50: 0.400 D60: 0.495 D85: 0.916 D90: 1.045 Cu: 2.824 Cc: 0.795

Query

Query Selections

Date Created 12/29/2023

Date Range 12/22/2023 - 12/29/2023

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping