




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FLDOT Silica Sand
Period 12/22/2023 - 12/29/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	3	100	0.0	95-100	95-100
#8 (2.36mm)	3	100	0.0	85-100	85-100
#16 (1.18mm)	3	92	2.1	67-96	65-97
#30 (.6mm)	3	55	5.1	27-68	25-70
#50 (.3mm)	3	17	3.6	7-33	5-35
#100 (.15mm)	3	1	0.0	0-6	0-7
#200 (75µm)	3	0	0.0	0-4	0-4
Pan	3	0	0.0		
FM	3	2.35	0.101	2.3	2.1-2.5
Total Moisture	3	4.3	0.95		



Tests: 1 D10(ES): 0.222 D15: 0.275 D30: 0.380 D50: 0.548 D60: 0.657 D85: 1.038 D90: 1.138 Cu: 2.968 Cc: 0.993

Query

Query Selections

Date Created 12/29/2023

Date Range 12/22/2023 - 12/29/2023

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping

Agency Florida DOT MAC