




Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1008-Mason Sand
Specification Mason Sand
Period 12/22/2023 - 12/29/2023

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100	0.0	97-100	
#8 (2.36mm)	4	100	0.0	97-100	
#16 (1.18mm)	4	100	0.0	90-100	
#30 (.6mm)	4	97	1.0	65-100	
#50 (.3mm)	4	88	0.5	35-90	
#100 (.15mm)	4	16	3.9	0-40	
#200 (75µm)	4	0.2	0.10		
Pan	4	0.0	0.00		
FM	4	0.99	0.041		
Total Moisture	4	4.9	1.00	0-6\3	0-7



Tests: 1 D10(ES): 0.115 D15: 0.144 D30: 0.172 D50: 0.208 D60: 0.229 D85: 0.291 D90: 0.350 Cu: 1.987 Cc: 1.115

Query

Query Selections

Date Created 12/29/2023

Date Range 12/22/2023 - 12/29/2023

Plant Haines City Mine (FDOT Pit #16-024)

Sample Type Shipping