



01/02/2024

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-298) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#30 (.6mm)	99	%	
	#50 (.3mm)	87	%	
	#100 (.15mm)	17	%	
	#200 (75µm)	0.4	%	
ASTM C-136	FM	0.975		
ASTM C-566	Total Moisture	6.522	%	0.000-6.000
	D10 (ES)	0.11	mm	
	D50	0.21	mm	
	D60	0.23	mm	
	Cc	1.13		
	Cu	2.04		

Sincerely,

Mario Cardenas
Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 863-424-0730 ext.515
Cell: 863-557-0342



01/02/2024

Name/Title

David Clements / Mine manager